

657(*) SW4 0.6/1 kV

EPR/ZH

BS 6883

Flame retardant, halogen-free, offshore & shipboard power, control & lighting cables with elastomeric insulation and sheath

CONSTRUCTION

Conductors	Tinned annealed circular stranded copper	
	Class 5 acc. to BS EN 60228	Class 2 acc. to BS EN 60228
	¹⁾ For sizes: 1.0 ÷ 1.5 mm ²	²⁾ For sizes 2.5 mm ² and above
Insulation	Halogen-free elastomer compound EPR type GP4 acc. to BS 7655-1.2	
Core identification ³⁾	All cores are white with black printed numbers	
Outer sheath	Heat-resistant, oil-resisting and flame-retardant elastomer compound type SW4 acc. to BS 7655-2.6	
Colour of outer sheath	Black	
Cable marking	ELECTRIC CABLE Type SW4 "number of cores" "x" "conductor size" "600/1,000 V" "TFK3" "BS6883" "UK00A code" "IEC60332-3-22 cat. A" "year" "metre mark"	

¹⁾Class 2 conductors for sizes below 2.5 mm² are available on request.

²⁾Class 5 flexible conductors for sizes above 2.5 mm² are available on request.

³⁾Coloured cores are available on request.



CHARACTERISTIC

Maximum conductor operating temperature:	+90°C	
Lowest ambient temperature for fixed installation:	-40°C	
Lowest installation temperature:	-15°C	
Minimum bending radius:	Overall diameter of cable (D)	Minimum bending radius
	≤ 10 mm	3 D
	16-25 mm	4 D
	> 25 mm	6 D
	D – overall diameter of cable	

657(*) SW4 0.6/1 kV

EPR/ZH

BS 6883

Fire performance

Flame retardant:	IEC 60332-3-22 Category A
Smoke emission:	BS EN 61034-2, IEC 61034-2
Corrosive gas emission:	BS EN 50267-2-1, IEC 60754-1: type SW4 cables ≤ 0.5% HCl
UV resistant:	UL 1581

131

Applications

Power, control or lighting cable for fixed installations in all areas and open deck in ships and offshore units.

Approvals

LR
Details related to particular Approvals are informative only. Please contact manufacturer to confirm whether the required cross-sections are covered by the Certificate.

Standard length cable packing:	1,000 m on drums Other forms of packing and delivery are available on request
--------------------------------	--

Number and cross-sectional area of conductor	Class of conductor	Nominal thickness of insulation	Nominal thickness of outer sheath	Approximate overall diameter of cable	Approximate net weight of cables SW4	UK00A Code
n × mm ²		mm	mm	mm	kg/km	
1 × 1	5	0.8	1.0	4.8	34	WF101
1 × 1.5	5	0.8	1.0	5.1	40	WF102
1 × 2.5	2	0.8	1.0	5.6	54	WF103
1 × 4	2	1.0	1.0	6.7	78	WF104
1 × 6	2	1.0	1.0	7.3	101	WF106
1 × 6	5	1.0	1.0	7.1	96	–
1 × 10	2	1.0	1.0	8.2	144	WF110
1 × 16	2	1.0	1.1	9.5	216	WF116
1 × 25	2	1.2	1.2	11.5	328	WF125
1 × 35	2	1.2	1.2	12.6	429	WF135

657(*) SW4 0.6/1 kV

EPR/ZH

BS 6883

Number and cross-sectional area of conductor	Class of conductor	Nominal thickness of insulation	Nominal thickness of outer sheath	Approximate overall diameter of cable	Approximate net weight of cables SW4	UK00A Code
1 × 50	2	1.4	1.3	14.3	551	WF150
1 × 70	2	1.4	1.3	16.1	753	WF170
1 × 95	2	1.6	1.4	18.6	1,049	WF195
1 × 120	2	1.6	1.5	20.3	1,274	WF10A
1 × 150	2	1.8	1.6	22.5	1,568	WF10B
1 × 185	2	2.0	1.7	25.0	1,949	WF10C
1 × 240	2	2.2	1.8	28.0	2,530	WF10D
1 × 300	2	2.4	1.9	31.1	3,134	WF10E
1 × 400	2	2.6	2.0	34.6	4,258	WF10F
1 × 500	2	2.8	2.2	38.8	5,337	WF10G
1 × 630	2	2.8	2.2	42.9	6,533	WF10H
2 × 1	5	0.8	1.0	8.1	86	WF201
2 × 1.5	5	0.8	1.1	8.5	103	WF202
2 × 2.5	2	0.8	1.1	9.5	140	WF203
2 × 4	2	1.0	1.2	11.7	210	WF204
2 × 6	2	1.0	1.2	12.8	270	WF206
2 × 10	2	1.0	1.3	14.9	391	WF210
2 × 16	2	1.0	1.4	17.4	574	WF216
2 × 25	2	1.2	1.5	21.1	864	WF225
2 × 35	2	1.2	1.6	23.7	1,129	WF235
2 × 50	2	1.4	1.7	26.8	1,452	WF250
2 × 70	2	1.4	1.9	30.7	1,991	WF270
2 × 95	2	1.6	2.1	35.8	2,766	WF295
2 × 120	2	1.6	2.2	39.1	3,338	WF20A
2 × 150	2	1.8	2.3	43.1	4,097	WF20B
3 × 1	5	0.8	1.1	8.4	100	WF301
3 × 1.5	5	0.8	1.1	9.0	122	WF302
3 × 2.5	2	0.8	1.1	10.1	169	WF303
3 × 4	2	1.0	1.2	12.4	257	WF304
3 × 6	2	1.0	1.2	13.6	335	WF306
3 × 10	2	1.0	1.3	15.9	490	WF310
3 × 16	2	1.0	1.4	18.6	732	WF316
3 × 25	2	1.2	1.6	22.7	1,121	WF325
3 × 35	2	1.2	1.7	25.4	1,474	WF335

657(*) SW4 0.6/1 kV

EPR/ZH

BS 6883

133

Number and cross-sectional area of conductor	Class of conductor	Nominal thickness of insulation	Nominal thickness of outer sheath	Approximate overall diameter of cable	Approximate net weight of cables SW4	UK00A Code
3 × 50	2	1.4	1.8	28.9	1,893	WF350
3 × 70	2	1.4	2.0	33.0	2,611	WF370
3 × 95	2	1.6	2.2	38.5	3,638	WF395
3 × 120	2	1.6	2.3	41.8	4,400	WF30A
3 × 150	2	1.8	2.5	46.5	5,425	WF30B
3 × 185	2	2.0	2.7	51.9	6,754	WF30C
3 × 240	2	2.2	2.9	58.7	8,770	WF30D
4 × 1	5	0.8	1.1	9.1	122	WF401
4 × 1.5	5	0.8	1.1	9.8	149	WF402
4 × 2.5	2	0.8	1.1	11.0	210	WF403
4 × 4	2	1.0	1.2	13.6	321	WF404
4 × 6	2	1.0	1.3	15.2	428	WF406
4 × 10	2	1.0	1.4	17.6	627	WF410
4 × 16	2	1.0	1.5	20.6	940	WF416
4 × 25	2	1.2	1.7	25.3	1,442	WF425
4 × 35	2	1.2	1.8	28.2	1,899	WF435
4 × 50	2	1.4	1.9	32.1	2,439	WF450
4 × 70	2	1.4	2.1	36.7	3,370	WF470
4 × 95	2	1.6	2.3	42.8	4,700	WF495
4 × 120	2	1.6	2.5	46.7	5,710	WF40A
4 × 150	2	1.8	2.7	51.9	7,035	WF40B
5 × 1.5	5	0.8	1.1	10.7	180	–
5 × 2.5	2	0.8	1.2	12.2	260	–
5 × 4*	2	1	1.3	15.2	394	–
5 × 6*	2	1	1.4	16.9	463	–
5 × 10*	2	1	1.5	19.6	685	–
5 × 35*	2	1.2	1.9	31.3	2,114	–
5 × 50*	2	1.4	2	35.6	2,709	–
6 × 1.5*	2	0.8	1.2	12.0	226	–
6 × 1.5*	5	0.8	1.2	11.8	214	–
6 × 2.5*	2	0.8	1.2	13.3	305	–
7 × 1.5	5	0.8	1.2	12.8	252	WF702
7 × 2.5	2	0.8	1.2	14.4	359	WF703
9 × 1.5*	5	0.8	1.3	14.9	304	–

657(*) SW4 0.6/1 kV

EPR/ZH

BS 6883

Number and cross-sectional area of conductor	Class of conductor	Nominal thickness of insulation	Nominal thickness of outer sheath	Approximate overall diameter of cable	Approximate net weight of cables SW4	UKOOA Code
10 × 1.5*	2	0.8	1.3	15.4	347	–
10 × 1.5*	5	0.8	1.3	15.1	326	–
12 × 1.5	5	0.8	1.3	15.6	370	WFA02
12 × 2.5	2	0.8	1.4	17.9	543	WFA03
19 × 1.5	5	0.8	1.4	19.4	570	WFB02
19 × 2.5	2	0.8	1.5	22.2	842	WFB03
27 × 1.5	5	0.8	1.6	22.4	766	WFC02
27 × 2.5*	5	0.8	1.7	25.5	1,082	–
37 × 1.5	5	0.8	1.7	26.2	1,107	WFD02

*Based on standard

Please refer to technical section for additional information relating to these cables.